

TECHNICAL PROPERTIES		ARIZONA
PHYSICAL		
Width		137-140 cm
Thickness		± 1,2 mm
Composition	Coating Backing	PU top Polyester
STRENGTH		
Tear strength	ISO 4674-1	≥ 25 N/5 cm (warp) ≥ 25 N/5 cm (weft)
Martindale	ISO 12947-2	≥ 100,000 cycles
Tensile strength	ISO 1421	≥ 220 N/3 cm (warp) ≥ 220 N/3 cm (weft)
Flexing test	DIN 53351	≥ 100,000 flexes (25 °C)
Bonding	ASTM D 751A	≥ 29 N (warp) ≥ 26 N (weft)
Hydrolysis resistance		≥ 5 weeks 70 °C * 95% RH
Colour fastness	ISO 105-B02	≥ 4 dry ≥ 3,5 wet / perspiration



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

www.wildeman-waalwijk.nl