

TECHNICAL PROPERTIES		AROME
PHYSICAL		
Width		138-140 cm
Length		30 m
Weight	DIN EN ISO 2286	± 540 gr/m ²
Composition	Coating (78%) Backing (22%)	100% PVC 75% Polyester, 25% Cotton
Thickness	DIN EN ISO 2286	± 0,8 mm
STRENGTH		
Martindale	DIN EN ISO 5470-2	≥ 50.000 cycles
Tear strength	DIN EN ISO 4674-1 Warp Weft	≥ 50 N ≥ 50 N
Tensile strength	DIN EN ISO 1421 Warp Weft	≥ 280 N ≥ 365 N
Elongation	DIN EN ISO 1421 Warp Weft	≥ 17% ≥ 27%
Colour fastness to rubbing	DIN EN ISO 105-X12 Dry & Wet	≥ 4 (Blue scale)
SAFETY		
Flame-retardant (UK)	BS 5852, 1&2	Passed



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

www.wildeman-waalwijk.nl