

TECHNICAL PROPERTIES

PROPERTY	METHOD		CURACAO	
Width	DIN 53352		150 cm	
Length			35-40 lm	
Weight			245 gr/m2 ± 5%	
Composition			100% Olefin Fabric	Backing (18%) Cotton
Tensile strength	ASTM D5034		Warp ≥73,70 kg.	Weft ≥72,35 kg.
Tear strength	ASTM 1424		Warp ≥5,12 kg	Weft ≥5,12 kg
Abrasion Resistance	ASTM D4157		≥9.000 cycles	
Light Fastness	ISO 105-B02		7/8 blue scale	
UV Factor Protection	AS/NZS 4399		Excellent 50+ (>128)	
Water Repellency	AATCC22-2005		4-5 (wet + dry)	
Resistance to Weathering	ASTM G154-12a		Class 4,0	
	UVA 340 Bulb			

