

TECHNICAL PROPERTIES

PROPERTY	METHOD	FLORES
Width	DIN 53352	140 cm +/- 3%
Length		25 lm
Weight		529 gr/m2 ± 5%
Composition		48%CO-15%VI-7%LI-30%PL
Pilling	UNI EN ISO 12945-2	Grade 4
Abrasion Resistance	UNI EN ISO 12947-2	≥52.000 cycles +/- 10%
Light Fastness	UNI EN ISO 105-B02	4-5 Blue Scale
Dry clean fastness	UNI EN ISO D01	Colour change 4-5
Rubbing fastness	UNI EN ISO 105-X12	Dry 4-5 Wet 2-3
Flame Retardant	EN 1012 1	Passed
Flame Retardant	BS 5852 1	Passed
Flame Retardant	CAL TB 117	Passed
Resistance to temperatures	Bleach 4,5 cl/l JIS Z 2837:2000 EN ISO 846A	From -20°C to 70°C
Resistance to alcohol 96%		Good
Resistance to cleaning agents		Good
Resistance to bacteria		Sanitized
Resistance to fungi		Sanitized