

TECHNICAL PROPERTIES		HAWAII
PHYSICAL		
Raw material		European cow
Brand mark(s)		No
Hump(s)		No
Substance	DIN EN ISO 2589 (IULTCS/IUP 4)	± 1,0 mm
Average size		± 5,0 m2
Dyeing		Drum dyed
Grain		Corrected Madras
STRENGTH		
Flexometer test	DIN EN ISO 5402 (IULTCS/IUP 402)	≥ 50,000 cycles
Tear strength	DIN EN ISO 3377-1 (IULTCS/IUP40)	≥ 30 N
Colour fastness to light	DIN EN ISO 105-B02 (IULTCS/IUF 402)	≥ 5 (Blue Scale)
Colour fastness to rubbing	DIN EN ISO 11640 (IULTCS/IUF 450)	
	Dry	≥ 4, 500 cycles
	Wet	≥ 4, 250 cycles
	Perspiration (pH8)	≥ 4, 80 cycles
Adhesion	DIN EN ISO 11644 (IULTCS/IUF 470)	≥ 3 N/cm
SAFETY		
Flame-retardant (UK)	BS 5852, 1	Passed
Flame-retardant (IMO)	A652 (16)	Passed
COMPLIANCE		
Reach	Free of harmful substances	Complies
IMO 0575	Marine equipment	Complies
ISO 14001	Environmental management	Complies
ISO 9001	Quality management	Complies
ISO TS 16949	Automotive production	Complies



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 650 419 | info@vanleeuwenleder.nl

www.vanleeuwenleder.nl