

TECHNICAL PROPERTIES		HOME SAND
PHYSICAL		
Width		152 cm
Length		50 m
Weight	DIN 53352	± 270 gr/m ²
Composition		100% Solution dyed acrylic fibre
STRENGTH		
Martindale	EN ISO 12947-2	≥ 17.000 cycles
Tensile strength	UNI EN ISO 13934-1 Warp Weft	≥ 1.900 N ≥ 800 N
Elongation	UNI EN ISO 13934-1 Warp Weft	≥ 28% ≥ 23%
Colour fastness to light	DIN 75202	≥ 8 (Blue scale) 4-5 (Grey scale)
Resistance to bleach	Ratio bleach/water= 1:4	Passed
Resistance to seam slippage	EN ISO 13936-2 Warp Weft	≥ 180 N/4 mm ≥ 180 N/3 mm
SAFETY		
Flame-retardant (UK)	BS 5852-1	Passed
Resistance to oil and water	Teflon finish	Passed
Resistance to water penetration	UNI EN 24920, dry surface	ISO 5 (100)



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

www.wildeman-waalwijk.nl