

TECHNICAL PROPERTIES		OTTOMANO
PHYSICAL		
Width		152 cm
Length		50 m
Weight	DIN 53352	± 320 gr/m ²
Composition		100% Solution dyed outdoor acrylic
STRENGTH		
Martindale	EN ISO 12947-2	≥ 10.000 cycles
Tensile strength	UNI EN ISO 13934-1 Warp Weft	≥ 1.900 N ≥ 610 N
Elongation	UNI EN ISO 13934-1 Warp Weft	≥ 35,5% ≥ 13%
Colour fastness to light	DIN 75202	≥ 8 (Blue scale) 4-5 (Grey scale)
Resistance to pilling	UNI EN ISO 12945-2	≥ 4, 2.000 cycles
Resistance to seam slippage	EN ISO 13936-2 Warp Weft	± 4,0 mm ± 3,0 mm
Resistance to shrinking	30°C water Warp Weft	≥ 2% ≥ 2%
SAFETY		
Flame-retardant (UK)	BS 5852-1	Passed
Resistance to oil and water	Teflon finish	Passed



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

www.wildeman-waalwijk.nl