

TECHNICAL PROPERTIES		STONE
PHYSICAL		
Raw material		South African cow hides
Brand mark(s)		Possible
Hump(s)		No
Substance	DIN EN ISO 2589 (IULTCS/IUP 4)	± 1,0 mm
Average size		± 4,0 m²
Dyeing		Drum dyed
Grain		Natural, stone washed
STRENGTH		
Flexometer test	EN ISO 5402	≥ 30.000 cycles
Tear strength	EN ISO 3377-1	≥ 20 N
Adhesion	EN ISO 11644	≥ 5 N/cm
Colour fastness to light	DIN EN ISO 105-B02	≥ 7 (Blue scale)
Colour fastness to rubbing	DIN 11640	
	Dry	≥ 800 cycles
	Wet	≥ 150 cycles



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 650 419 | info@vanleeuwenleder.nl

www.vanleeuwenleder.nl