

TECHNICAL PROPERTIES		SUNSTOP
PHYSICAL		
Composition		100% Polyester
Thread construction		Continuous filament
Count	10	NoTkt 10-dtex2700(3)-tex270
	15	NoTkt 15-dtex2100(3)-tex210
	20	NoTkt 20-dtex1350(3)-tex135
	30	NoTkt 30-dtex900(3)-tex90
	40	NoTkt 40-dtex700(3)-tex70
STRENGTH		
Breaking strength	10	≥ 19,300cN
	15	≥ 13,600cN
	20	≥ 8,600cN
	30	≥ 6,000cN
	40	≥ 4,500cN
Elongation	10	Ø16%
	15	Ø16%
	20	Ø14%
	30	Ø15%
	40	Ø14,5%
Colour fastness to light	ISO 105-B02	Grade 4 or better
Colour fastness to rubbing	ISO 105-X12	Grade 4 or better
Colour fastness to dry clean	ISO 105-D01	Grade 4 or better
Colour fastness to water	ISO 105 E01	Grade 4 or better
Colour fastness to chlorinated water	DIN EN ISO 20105-N01	Grade 4 or better
Colour fastness to washing	ISO 105 C10 C	Grade 4 or better
Perspiration fastness	ISO 105-E04	Grade 4 or better
Shrinking in boiling water (30 min)		≥ 2%
Shrinking at 160°C (30 min)		≥ 4%



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

www.wildeman-waalwijk.nl