

TECHNICAL PROPERTIES		SUPREME BUTTERSOF
PHYSICAL		
Raw material		European bull
Brand mark(s)		No
Hump(s)		No
Thickness	EN ISO 2589 (IULTCS/IUP 4)	± 1,5 mm
Average size		± 5,5 m2
Dyeing		Semi aniline drum dyed
Grain		Corrected Dollaro Americano
STRENGTH		
Flexometer test	ISO 5402-1 (IULTCS/IUP 20)	≥ 20,000 cycles
Tear strength	ISO 3377-1 (IULTCS/IUP 40)	≥ 20 N
Adhesion	ISO 11644 (IULTCS/IUF 470)	≥ 1,5 N/cm
Colour fastness to light	ISO 105-B02	≥ 5 (Blue Scale)
Colour fastness to rubbing	ISO 11640 (IULTCS/IUF 450)	
	Dry	≥ 5, 500 cycles
	Wet	≥ 4, 80 cycles
	Perspiration (pH8)	≥ 4, 50 cycles
SAFETY		
Flame-retardant (UK)	BS 5852	Passed
	EN 1021, 1 & 2	Passed
COMPLIANCE		
Reach	Free of harmful substances	Complies
Blue Angel	Environmental friendly	Complies
ISO 14001	Environmental management	Complies
ISO 9001	Quality management	Complies



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 650 419 | info@vanleeuwenleder.nl

www.vanleeuwenleder.nl