

TECHNICAL PROPERTIES		TOSCA
PHYSICAL		
Raw material		Central European bull
Substance	DIN EN ISO 2589 (IULTCS/IUP 4)	± 1,4 mm
Average size		± 5,0 m2
Dyeing		Aniline
Grain		Natural grain
STRENGTH		
Flexing endurance	ENI EN ISO 5402 DRY 50,000	No damage
Tear strength	UNI EN ISO 3377-1	≥ 20 N
Colour fastness to light	UNI EN ISO 105-B02	≥ 2 (Blue Scale)
Colour fastness to rubbing	UNI EN ISO 11640 (IULTCS/IUF 450) Dry	≥ 3 (Grey Scale) 50 cycles
Adhesion	ISO 11644 (IULTCS/IUF 470)	≥ 2,5 N/cm
SAFETY		
Flame-retardant (UK)	BS 5852	Passed
	EN 1021, 1 & 2	Passed
COMPLIANCE		
Reach	Free of harmful substances	Complies
LWG	Environmental Protocol	Gold Rated
ISO 14001	Environmental management	Complies
ISO 9001:2015	Quality management	Complies



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 650 419 | info@vanleeuwenleder.nl

www.vanleeuwenleder.nl