

TECHNICAL PROPERTIES		BATYLINE CANATEX
PHYSICAL		
Width		180 cm
Length		50 m
Weight	EN ISO 2286-2	± 560 gr/m ²
Composition		23% Polyester 77% PVC flame-retardant & hemp fibres
Openess factor		21%
STRENGTH		
Martindale	EN ISO 14465	≥ 120.000 cycles
Wyzenbeek	ASTM D4157	≥ 600.000 double rubs
Tensile strength	EN ISO 1421 Warp Weft	≥ 235 N/5cm ≥ 235 N/5cm
Elongation	EN ISO 1421 Warp Weft	≥ 3% ≥ 3%
Resistance to temperatures		-30 °C / +70 °C
SAFETY		
Flame-retardant (IMO)	IMO MSC.307 (88) Annex 1 Part 8	Passed
Resistance to weathering	ASTM G154: UVA 340	4-5 (700h)
Resistance to mould	IMO MSC.307 (88) Annex 1 Part 8	Passed
COMPLIANCE		
LOOP certified	Recycled/bio based materials	Complies
Green Guard	Free of chemical emissions	Complies
Free of phthalates	Free of chemical plastifiants	Complies



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 235 028 | info@wildeman-benelux.nl

www.wildeman-benelux.nl