

TECHNICAL PROPERTIES		CURAÇÃO
PHYSICAL		
Width		150 cm
Length		35-40 m
Weight		± 245 gr/m ²
Composition	Coating Backing	100% Olefin fabric 18% Cotton
STRENGTH		
Martindale	ASTM D4157	≥ 9.000 cycles
Tear strength	ASTM 1424	
	Warp Weft	≥ 5,12 kg ≥ 5,12 kg
Tensile strength	ASTM D5034	
	Warp Weft	≥ 73,70 kg ≥ 72,35 kg
Colour fastness to light	ISO 105-B02	7-8
SAFETY		
UV Factor Protection	AS/NZS 4399	Excellent, 50+ (>128)
Resistance to water	AATCC22-2005	
	Wet Dry	4-5 4-5
Resistance to weathering	ASTM G154-12a, Class 4.0 (UVA 340 Bulb)	Passed



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

www.wildeman-waalwijk.nl