

TECHNICAL PROPERTIES		CURAÇÃO MIXED
<b>PHYSICAL</b>		
Width		150 cm
Length		35-40 m
Weight		± 245 gr/m <sup>2</sup>
Composition	Coating	100% Olefin fabric
	Backing	18% Cotton
<b>STRENGTH</b>		
Martindale	ASTM D4157	≥ 9.000 cycles
Tear strength	ASTM 1424	
	Warp	≥ 5,12 kg
	Weft	≥ 5,12 kg
Tensile strength	ASTM D5034	
	Warp	≥ 73,70 kg
	Weft	≥ 72,35 kg
Colour fastness to light	ISO 105-B02	7-8
<b>SAFETY</b>		
UV Factor Protection	AS/NZS 4399	Excellent, 50+ (>128)
Resistance to water	AATCC22-2005	
	Wet	4-5
	Dry	4-5
Resistance to weathering	ASTM G154-12a, Class 4.0 (UVA 340 Bulb)	Passed



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

[www.wildeman-waalwijk.nl](http://www.wildeman-waalwijk.nl)