

TECHNICAL PROPERTIES		SAMAR
PHYSICAL		
Raw material		Brazilian cow hides
Substance	EN ISO 2589 (IULTCS/IUP 4)	± 1,5 mm
Average size		± 5,0 m ²
Dyeing		Semi aniline
Grain		Slightly corrected
STRENGTH		
Tear strength	ISO 3377-1 (IULTCS/IUP40)	≥ 20 N
Adhesion	DIN EN ISO 11644 (IULTCS/IUF 470)	≥ 2 N/cm
Colour fastness to light	DIN EN ISO 105-B02 (IULTCS/IUF 402)	≥ 3 (Blue scale)
Colour fastness to rubbing	DIN EN ISO 11640 (IULTCS/IUF 450)	
	Dry	≥ 4, 500 cycles (Grey scale)
	Wet	3-4, 250 cycles (Grey scale)
	Perspiration (pH8)	3-4, 80 cycles (Grey scale)
SAFETY		
Flame-retardant (UK)	BS 5852, 1 & 2	Passed
	EN 1021, 1 & 2	Passed
Flame-retardant (US)	TB 117-2013	Passed (on request)
COMPLIANCE		
Reach	Free of harmful substances	Complies



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 650 419 | info@vanleeuwenleder.nl

www.vanleeuwenleder.nl