

TECHNICAL PROPERTIES		SANTORINI
PHYSICAL		
Width		140 cm
Length		50 m
Weight		± 450 gr/m ²
Composition		100% Recycled yarn
STRENGTH		
Martindale	EN ISO 12947, 1&2	≥ 40.000 cycles
Tensile strength	EN ISO 13934-1 Warp Weft	≥ 1497 N 36,9% ≥ 1569 N 34,9%
Colour fastness to light	EN ISO 105-B02	≥ 5
Colour fastness to rubbing	EN ISO 105-X12 Dry & Wet	≥ 4
Colour fastness to chlorinated water	EN ISO 105-E03	4-5
Colour fastness to salt water	EN ISO 105-E02	4-5
Colour fastness to artificial weathering	EN ISO 105-B04	≥ 7
Colour fastness to acid & alkaline perspiration	ISO 105-E04	4-5
Resistance to seam slippage	EN ISO 13936-2 Warp Weft	≥ 2,0 mm ≥ 2,0 mm
Resistance to tear growth	EN ISO 13937-3 Warp Weft	≥ 134,6 N ≥ 131,3 N
Snagging Test - Rotating Chamber method	BS 8479, 2000 turns	≥ 5
SAFETY		
Flame-retardant (UK)	EN 1021, 1 BS 5852, 1	Passed Passed
Flame-retardant (US)	CA TB 117	Passed
Flame-retardant	NFPA 260	Passed
Resistance to cold cracking	-23°C	Passed
COMPLIANCE		
Reach	Free of harmful substances	Complies
Blue World		Complies
Global Recycled Standard		Complies



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

www.wildeman-waalwijk.nl