

| TECHNICAL PROPERTIES | | BATYLINE [STAM] SKIN TOP |
|-----------------------------|-----------------------------------|------------------------------|
| PHYSICAL | | |
| Width | | 140 cm |
| Length | | 20 m |
| Weight | EN ISO 2286-2 | ± 780 gr/m ² |
| Composition | Coating Backing | Multiple layers Polyamide |
| Thickness | EN ISO 5084 | ± 1,1 mm |
| STRENGTH | | |
| Martindale | EN ISO 5470-2 | ≥ 120,000 cycles |
| Flexometer test | EN ISO 7854 | ≥ 400,000 cycles |
| Tear strength | EN ISO 13937-1 Warp Weft | ≥ 25 N ≥ 15 N |
| Tensile strength | EN ISO 1421 Warp Weft | ≥ 440 N ≥ 280 N |
| Elongation | EN ISO 1421 Warp Weft | ≥ 35% ≥ 55% |
| Colour fastness to UV light | ASTM G154 (1250h) | ≥ 4 |
| Resistance to temperatures | | -20 °C / +70 °C |
| SAFETY | | |
| Flame-retardant (UK) | BS 5852, Crib 5 EN 1021, 1 & 2 | Passed Passed |
| Flame-retardant (US) | NFPA 260 CAL TB 117 | Passed Class 1 |
| Flame-retardant (IT) | UNI 9177-87 | Class 2 |
| Flame-retardant (CHE) | SN 198898 - VKF / AEAI | 5.3 |
| Flame-retardant (DE) | DIN 53438-3 | Class F1 |
| Flame-retardant (FRA) | NF P 92-507 NF P 16-101-102 | M2 F4 |
| Flame-retardant (AUS) | AS / NZS 1530-3 AS / NZS 3837 | Passed Group 2 |
| Flame-retardant (IMO) | MSC.307 (88), Annex 1 Part 8 | Passed |
| Resistance to funghi | ISO 846 | Passed |
| Aeronautical test | FAR/JAR 25-853/855 | Passed |
| COMPLIANCE | | |
| Reach | Free of harmful, substances | Complies |
| ISO 14001 | Environmental management | Complies |
| Sanitized® | | Complies |
| Free of phthalates | | Complies |



Wildeman



van Leeuwen

Van Hilststraat 1 | 5145 RK Waalwijk | Netherlands

+31 (0) 416 333 651 | info@wildeman-waalwijk.nl

www.wildeman-waalwijk.nl