

Sunstop

TECHNICAL PROPERTIES

PROPERTY	METHOD	SUNSTOP
Material		100% polyester
Tread construction		Continuous filament
Count		
10		No/Tkt 10-dtex2700(3)-tex270
15		No/Tkt 15-dtex2100(3)-tex210
20		No/Tkt 20-dtex1350(3)-tex135
30		No/Tkt 30-dtex900(3)-tex90
40		No/Tkt 40-dtex700(3)-tex70
Breaking strength		
10		>19300cN
15		>13600cN
20		>8600cN
30		>6000cN
40		>4500cN
Elongation		
10		Ø 16%
15		Ø 16%
20		Ø 14%
30		Ø 15%
40		Ø 14,5%
Boiling shrinkage (30min)		>2%
Thermal shrinkage 160°C/30min		>4%
Wash fastness	ISO 105 C10 C	Grade 4 or better
Water fastness	ISO 105 E01	Grade 4 or better
Rub fastness	ISO 105 X12	Grade 4 or better
Hypochlorit fastness	DIN EN ISO 20105-N01	Grade 4 or better
Drycleaning fastness	ISO 105 D01	Grade 4 or better
Perspiration fastness	ISO 105 E04	Grade 4 or better
Light fastness	ISO 105-B02	Grade 4 or better

