

TECHNICAL PROPERTIES

PROPERTY	METHOD	SEQUOIA
Substance	DIN en ISO 2589, IUP 4	1,0 mm ±0,1
Average size		± 5,0 sqmt
Raw material		Central European cow
Dyeing		Aniline
Grain		Natural grain
Fastness to art. light	UNI EN ISO 105-B02	≥ 3 blue scale
Fastness to rubbing	UNI EN ISO 11640 Dry 50 Wet 20 Sweat 20	≥ 3/4 grey scale ≥ 3 grey scale ≥ 3 grey scale
Tear resistance	UNI EN ISO 3377-1	≥ 20 N
Flexing endurance	ENI EN ISO 5402	No damage
Finish Adhesion	UNI EN ISO 11644 Dry	≥ 2 N/cm
Flame retardant	EN 1021 1 + 2	Passed
Flame retardant	BS 5852	Passed
Reach	Free of harmful substances	Passed
ISO 14001	Environmental management	Passed
LWG	Environmental Protocol	Gold Rated
ISO 9001:2015	Quality management	Passed

