

TECHNICAL PROPERTIES

PROPERTY	METHOD	WELLINGTON
Substance	DIN en ISO 2589, IUP 4	1,0 – 1,2 mm
Average size		5,0 sqmt
Dyeing		Semi Aniline dyed
Grain		Corrected grain
Fastness to light	DIN EN ISO 105-B02, IUF 402	≥ 5
Fastness to rubbing	DIN EN ISO 11640, IUF 450	
	Dry	≥ 5
	Wet	≥ 5
	Sweat (pH8)	≥ 5
Flexometer test	DIN EN ISO 5402, IUP 402	≥ 50.000 cycles
Adhesion of finish	DIN EN ISO 11644, IUF 470	
Tear strength	DIN EN ISO 3377-1 IUP 40	≥ 30N
Flammability	BS 5852 1&2	Passed
Flammability	BS EN 1021 1&2 2006	Passed
Reach	Free of harmful substances	Complies
ISO 14001	Environmental management	Complies
ISO 9001:2008	Quality management	Complies