

TECHNICAL PROPERTIES

PROPERTY	METHOD	STONE
Raw material		South African cow
Brand mark		Possible brand marks
Hump		No hump
Substance	DIN en ISO 2589, IUP 4	1,0 mm
Average size		4,0 m2
Dyeing		Drum dyed
Grain		Natural grain, Stone washed effect
Fastness to light	DIN EN ISO 105-B02	> 7 Blue scale
Fastness to rubbing	DIN 11640 Dry Wet	> 800 cycles > 150 cycles
Adhesion strength	EN ISO 11644	> 5 N
Flex strength	EN ISO 5402	> 30.000 flexes
Tear strength	EN ISO 3377-1	> 20 N